

## UNDERSTANDING NANO-SCALE CATALYTIC EFFECTS

(completed September 2010)

*A technical investigation commissioned by the members of the **Catalytic Advances Program***

### CONTENTS

<b>1. INTRODUCTION</b> .....	<b>1</b>
<b>2. CATALYSIS AT THE NANOSCALE: DIFFERENCES FROM CLASSICAL CATALYSIS</b> .....	<b>5</b>
2.1 INTRODUCTION .....	5
2.2 SIMILARITIES AND DIFFERENCES .....	7
2.2.1 Historical Suggestions .....	7
2.2.2 Case Studies .....	9
2.2.2.1 Comparison of the synthesis of nanoparticle-based nanocatalysts from colloidal routes and catalysts synthesized by traditional methods (impregnation, exchange) .....	9
2.2.2.2 Comparison of the particle-size dependence of the hydrogenolysis of ethane on nanocatalysts and traditionally-prepared catalysts .....	12
2.2.2.3 Comparison of the oxidation of carbon monoxide on Au nanocatalysts .....	14
2.3 EXPERIMENTAL TECHNIQUES AND RESULTS DEMONSTRATING THE DIFFERENCES .....	16
2.3.1 Microscopy Observations .....	17
2.3.1.1 Structure of dendrimer-synthesized PdAu nanoparticles depends on the method of synthesis .....	17
2.3.2 Surface Science Observations .....	19
2.3.2.1 Reaction-Driven Restructuring of Rh-Pd and Pt-Pd Core-Shell Colloidal Nanoparticles .....	20
2.3.2.2 In Situ X-Ray Absorption Spectroscopy (XAS) Examination of the Influence of the Size of Co Nanoparticles on the Oxidation State of the Nanoparticle during Fischer-Tropsch Synthesis .....	21

2.3.2.3	Sum-frequency generation studies of 2-dimensional Model Nanocatalysts – CO Oxidation on Cubic Pt Nanoparticle Monolayers.....	22
2.3.3	Characterization Using Reactive Studies .....	25
2.4	COMPUTATIONAL AND THEORETICAL MODELING STUDIES AND PREDICTIONS.....	29
2.4.1	Ab-initio Density Functional Theory Calculations for New Bimetallic Catalyst Design .....	29
2.4.2	Examples of Ab-initio Driven Nanocatalyst Development – Combined Theory and Colloidal Synthesis .....	31
2.5	CONCLUSIONS, FUTURE NEEDS, AND DIRECTIONS .....	35
2.5.1	Conclusions .....	35
2.5.2	Future Needs .....	37
2.5.3	Future Directions.....	40
2.6	REFERENCES.....	42
<b>3.</b>	<b>NANOSCALE CATALYSTS AND SUPPORTS .....</b>	<b>55</b>
3.1	INTRODUCTION.....	55
3.2	UNIQUENESS OF NANOSCALE CATALYST AND SUPPORT PROPERTIES .....	55
3.2.1	Metal Functionality .....	56
3.2.1.1	Size.....	56
3.2.1.2	Shape.....	59
3.2.1.3	Composition.....	60
3.2.2	Support Materials .....	62
3.2.3	Metal-Support Interactions.....	63
3.2.4	Properties.....	64
3.2.4.1	Activity .....	64
3.2.4.2	Selectivity .....	65
3.2.4.3	Acidity Functionality.....	67
3.2.4.4	Porosity and Texture.....	68
3.2.4.5	Stability .....	70
3.3	TECHNIQUES NECESSARY TO PREPARE NANOCATALYSTS.....	75
3.3.1	Support Materials .....	76
3.3.1.1	Disordered Oxide Supports.....	76

3.3.1.2	Ordered Oxide Supports .....	79
3.3.2	Catalytic Metals and Metal Oxides .....	81
3.4	EXAMPLES OF NANOSCALE CATALYSTS AND PERFORMANCE CHARACTER.....	85
3.4.1	Water-Gas-Shift (WGS) Reaction.....	85
3.4.2	Catalytic Hydrogenation of Olefins .....	89
3.4.3	Oxidative Dehydrogenation of Alkanes to Olefins .....	92
3.5	CONCLUSIONS AND FUTURE DIRECTIONS .....	95
3.6	REFERENCES .....	98
<b>4.</b>	<b>NANO-SCALE IMPACTS ON TRADITIONAL CATALYTIC EFFECTS .....</b>	<b>119</b>
4.1.	INTRODUCTION.....	119
4.2.	EFFECT ON THE ACTIVE SITE.....	119
4.2.1	Size and Shape.....	120
4.2.2	Active Phase-Support Interface.....	124
4.2.3	Effect on Bulk Properties .....	125
4.3	EFFECTS DUE TO ACCESSIBILITY OF THE ACTIVE SITE .....	129
4.4	EFFECTS ATTRIBUTED TO CONFINEMENT IN NANO-SCALE .....	135
4.4.1	Effect of Charge Stabilization .....	135
4.4.2	Concentration Effect.....	136
4.4.3	Cooperative Effect.....	136
4.4.4	Tandem Reactions .....	140
4.4.5	Enhancing Catalyst Stability .....	141
4.5	OTHER EXAMPLES.....	142
4.6	OPPORTUNITIES, CHALLENGES, AND FUTURE DIRECTIONS.....	143
4.7	REFERENCES .....	144
<b>5.</b>	<b>INDEX .....</b>	<b>151</b>

## FIGURES

Figure 2.1	Evolution of model systems in heterogeneous catalysis (Somorjai, et al., 2007). .....	8
Figure 2.2	Flow diagram for [typical] syntheses of (A) traditional catalysts and (B) nanocatalysts. ....	10
Figure 2.3	(A) Transmission electron microscopy image of Pt/Al <sub>2</sub> O <sub>3</sub> reforming catalyst. (B) TEM image for 3.6 nm particles synthesized by the reduction of chloroplatinic acid in methanol in the presence of PVP. (C) TEM image for 7 nm particles synthesized by the reduction of chloroplatinic acid in refluxing ethylene glycol in the presence of PVP. (D, E, F) Corresponding particle size distribution of nanoparticles in (A), (B), and (C), respectively. (A) from (Boudart, et al., 1984a). (B) and (C) from (Rioux, et al., 2005). ....	11
Figure 2.4	Turnover frequency for ethane hydrogenolysis over a series of SBA-15 silica supported Pt nanocatalysts. The inset is an example of the particle size dependence of ethane hydrogenolysis for Pt catalysts synthesized by incipient wetness. The traditional catalysts demonstrate a maximum in activity, while the nanocatalyst displayed sympathetic structure sensitivity. Figure adapted from (Nazimek, et al., 1989; Song, et al., 2006b). ....	12
Figure 2.5	(A) The original particle size dependence for the low temperature oxidation of carbon monoxide over deposition-precipitation prepared TiO <sub>2</sub> -supported Au catalysts reported by Haruta (Haruta, et al., 1993). (B) The dependence of the rate of CO oxidation over a model catalyst, Au/TiO <sub>2</sub> (110)-(1 × 1). (C) Particle size distribution of the Au clusters supported on the TiO <sub>2</sub> (110)-(1 × 1) surface. Adapted from (Valden, et al., 1998). ....	14
Figure 2.6	(A) Method for the extraction of Au nanoparticles from the interior of dendrimers using small molecules (such as alkyl thiols) to form monolayer protected clusters (MPCs). (B, C) Electron microscopy images of WGC Au/TiO <sub>2</sub> standard catalyst and Au MPCs supported on TiO <sub>2</sub> . (D) A comparison of the oxidation of carbon monoxide over the TiO <sub>2</sub> -supported WGC and MPC catalysts at the same experimental conditions in a differential microreactor (Korkosz, et al., 2007). ....	15
Figure 2.7	The rate of formation of vinyl acetate on Au(111) and Au(100) as a function of Pd coverage. The insets are models of both surfaces containing dilute Pd concentrations. It is proposed that optimally spaced nearest-neighbor Pd (atoms) monomers are the active site for VA synthesis (Chen, et al., 2005). ....	18
Figure 2.8	Synthetic methods to form homogeneous alloy and core-shell nanoparticles in dendrimers. The co-complexation route led to the formation of PdAu alloy nanoparticles, while the sequential reduction of Pd and Au (irrespective of the order of reduction) led to the formation of Pd@Au coreshell nanoparticles (Weir, et al., 2010). ....	19

- Figure 2.9 (A,B) TEM images of as-synthesized  $Rh_{0.5}Pd_{0.5}$  and  $Pt_{0.5}Pd_{0.5}$  nanoparticles deposited on a copper TEM grid. (C, D) Synchrotron-based XPS depth profiling of the  $Rh_{0.5}Pd_{0.5}$  and  $Pt_{0.5}Pd_{0.5}$  nanoparticles. It is apparent that both nanoparticles had a core-shell architecture. (E, F) The influence of gas atmosphere (NO = oxidizing; NO + CO = reducing) on the surface composition of the  $Rh_{0.5}Pd_{0.5}$  and  $Pt_{0.5}Pd_{0.5}$  nanoparticles. Adapted from (Tao, et al., 2008). .....20
- Figure 2.10 (A) Transmission electron microscopy image of 5.3 nm cobalt nanoparticles which were supported on a Au foil to create a 2D model catalyst for XAS studies. (B) Particle size distribution of 5.3 nm (mean size) Co nanoparticles. (C, D) Co L-edge spectra of cobalt nanoparticles deposited over Au foils acquired *in-situ* during exposure to pure hydrogen at the stated temperatures. Particle diameters are (C) 3 and (D) 10 nm. (E, F) Co L-edge spectra for (E) cobalt foil and (F) 3 nm Co nanoparticles during treatment with CO or syngas ( $H_2 + CO$ ) at the stated temperature. Adapted from (Herranz, et al., 2009). .....22
- Figure 2.11 (A) Transmission electron microscopy (TEM) image of the cubic Pt nanoparticles supported on a carbon-copper TEM grid. (B) Schematic of *in-situ* SFG reaction cell showing a monolayer of PVP-capped Pt nanoparticles deposited onto a single-crystal sapphire prism by a LB technique. The spectroscopy cell operates as a recirculating batch reactor. A gas chromatography (GC) system, incorporated in the recirculation loop, is used for periodic sampling of the gas-phase composition. (C) SFG spectra (ssp polarization) of a monolayer consisting of PVP-capped Pt nanoparticles exposed to CO at 295 K before (black squares) and after (red circles) oxidation in  $O_2$  at 373 K for 3 h. Oxidation resulted in the removal of a significant fraction of the capping polymer, affecting the position and intensity of the CO peak. (D) Square root of the atop CO peak intensity in the SFG spectrum (ssp polarization) of a monolayer consisting of PVP-capped Pt nanoparticles vs time under flowing  $O_2$  at (black squares) 338 K, (red circles) 351 K, (blue triangles) 361 K, and (green upside-down triangles) 373 K. (E) Arrhenius plots of CO oxidation measured by the first-order exponential decay of the SFG intensity of the atop CO peak (blue triangles) and the accumulation of  $CO_2$  in the gas phase determined from GC measurements (black squares). The apparent activation energies calculated by the two independent methods are in good agreement with each other. Adapted from (Kweskin, et al., 2006). .....24
- Figure 2.12 (A) Scanning electron microscopy (SEM) image of 90 nm cubic Ag nanoparticles deposited on a Si wafer. (B) SEM image of 125 nm Ag nanowires deposited on a Si wafer. Inset is schematic image of the pentagonal nanowires. The ends of the nanowires are composed of (111) oriented surfaces, while the sides are composed of (100) surfaces. (C) The influence of particle size and shape on the selectivity to EO at various partial pressures of  $O_2$ . The reaction was conducted at 510 K under differential reactor conditions (2-4% conversion). (D) The selectivity to EO as a function of time for 350 nm nanocubes with 2 ppm vinyl chloride added to the feed. The reaction conditions were  $P_{O_2}/P_{ethylene}$  ratio of 3 and a temperature of 510 K. The steady-state

- ethylene conversion was 3 %. (E) Potential energy surfaces for transformation of OMC to AC and EO on Ag(111) (a) and Ag(100) (b). Energies are referenced to  $O_{ads}$  and ethylene<sub>(g)</sub> (c) OMC on Ag(111), (d) EO transition state on Ag(111), (e) AC transition state on Ag(111). Adapted from (Christopher, et al., 2008; Christopher, et al., 2010).....26
- Figure 2.13 TEM images of (A) TTAB-stabilized cubic Pt nanoparticles and (B) TTAB-stabilized cuboctahedral nanoparticles. The size distribution of (C) TTAB-stabilized cubic particles (average size:  $12.3 \pm 1.4$  nm, 79% cubes, 3% triangles, and 18% irregular shapes) and (D) size distribution of TTAB-stabilized cuboctahedral particles (average size:  $13.5 \pm 1.5$  nm, 90% cuboctahedra and 10% irregular shapes). (E) Turnover rates of cyclohexane ( $C_6H_{12}$ ) and cyclohexene ( $C_6H_{10}$ ) formation on TTAB-stabilized cubic and cuboctahedral Pt nanoparticles. Reaction conditions are 10 Torr  $C_6H_6$ , 100 Torr  $H_2$ , and 650 Torr Ar. (F) Turnover rates of  $C_6H_{12}$  and  $C_6H_{10}$  formation on Pt(100) and Pt(111) single-crystals. Reaction conditions are the same as those reported in (E). Adapted from (Bratlie, et al., 2007). .....27
- Figure 2.14 (A) TEM images of catalysts comprised of cubic platinum nanoparticles loaded onto a silica xerogel and calcined at different temperatures up to 575 K. (B) Statistical analysis of the size and shape of the supported cubic-Pt nanocatalysts derived from TEM pictures such as those shown in (A). Narrow size distributions with an average nanoparticle size of 5.0 nm were obtained in all cases irrespective of the oxidation temperature used. In terms of shape, only approximately 60% of the nanoparticles supported on the silica are cubic, but most of those retained their shape upon oxidation to temperatures of up to 575 K. (C) Selectivity for the conversion of *cis*- (left columns in each pair) and *trans*- (right columns) 2-butenes on dispersed cubic (left panel) and tetrahedral (right) platinum nanoparticles as a function of reaction temperature. Adapted from (Lee, et al., 2010a).....28
- Figure 2.15 (A) Calculated energy diagrams for CO methanation over nickel, ruthenium and rhenium. Only the highest of the activation barriers for hydrogenation of C and O are included. (B) Brønsted–Evans–Polanyi relation for CO dissociation over transition metal surfaces. The transition state potential energy,  $E_a$ , is linearly related to the CO dissociation energy. (C) The corresponding measured volcano-relation for the methanation rate. (D) Pareto plot of the activity measure  $\frac{\Delta E_{diss}(M) - |E_{diss}(M) - E_{diss}(optimal)|}{E_{diss}(M)}$  and the cost for 117 elemental metals and bimetallic alloys of the form  $A_xB_{1-x}$  ( $x = 0, 0.25, 0.50, 1$ ). Each blue point corresponds to a particular alloy. The elemental metals are shown (black), and the Pareto optimal set is also indicated (red). (E) Measured rate of CO removal for a gas containing 2 % CO in 1 bar of  $H_2$  for 2.5% NiFe/MgAl<sub>2</sub>O<sub>4</sub> spinel catalyst. Adapted from (Andersson, et al., 2006; Norskov, et al., 2009).....30
- Figure 2.16 Schematic representation of a metal overlayer (left) and near-surface alloy (NSA) (right). The blue spheres represent the solute metal, while the yellow spheres represent the base metal. Adapted from (Greeley, et al., 2006). .....31

- Figure 2.17 (A) Metal alloys are denoted as solute/host pairs. The  $x$  axis indicates the energy ( $E_{\text{seg}}$ ) for a single solute atom to move from the bulk to the surface layer of the host metal. The  $y$  axis denotes the difference between the magnitudes of the hydrogen binding energies ( $\theta_{\text{H}} = 1/4$  monolayer) on the pure solute ( $|BE_{\text{H}}^{\text{sol}}|$ ) and on the pure host ( $|BE_{\text{H}}^{\text{host}}|$ ) close-packed metal surfaces. Regions in which hydrogen-induced segregation is expected are hatched. The  $*$  symbol denotes overlayers. (B) Binding energy of H ( $BE_{\text{H}}$ ) on various closed-packed surfaces. Binding energies are referenced to a clean metal slab and a gas-phase hydrogen atom ( $\text{H}(\text{g})$ ) at infinite separation from one another. The height of the bars associated with the various alloys and pure metals is arbitrary and is varied only for clarity. The vertical dashed line at  $-2.28$  eV corresponds to thermoneutral  $\text{H}_2(\text{g})$  dissociation (the gas-phase  $\text{H}_2$  bond energy is  $4.57$  eV). Adapted from (Greeley, et al., 2006). ..... 32
- Figure 2.18 TEM image of (A) Ru@Pt and (B) Pt-Ru alloy nanoparticles. The insets are HRTEM images (left), particle size histograms (bottom right), and ideal models of the particle types (right). Histograms were constructed by counting 200 particles. Each bar represents  $0.5$  nm diameter, and the dashed lines represent the average sizes, which are  $4.1$  nm and  $4.4$  nm, respectively. (C) Temperature-programmed reaction spectroscopy results for the different Pt–Ru catalysts showing  $\text{H}_2\text{O}$  formation versus temperature for  $\text{H}_2$  feeds contaminated by  $0.1\%$  CO by volume. The  $\text{H}_2\text{O}$  yields are plotted as % maximum formation based on the limiting reactant  $\text{O}_2$ . The monometallic Pt remains on the baseline in this temperature range and does not light off until  $170^\circ\text{C}$ . (D) The percent formation of  $\text{H}_2\text{O}$  (open symbols) and % CO conversion (filled symbols) plotted against temperature for the core–shell (black) and alloy (red) nanoparticles catalysts for  $\text{H}_2$  feeds contaminated by  $0.2\%$  CO. Adapted from (Alayoglu, et al., 2008). .... 33
- Figure 2.19 Differential binding energy for CO as a function of CO coverage on various Pt\*/M model (111) or (0001) surfaces. A positive differential BE indicates that the respective state is not stable on the surface. From (Nilekar, et al., 2010). ..... 35
- Figure 2.20 Reaction sequence for the hydrogenation of crotonaldehyde. The major pathways are the hydrogenation of the  $\text{C}=\text{C}$  double bond to form the aldehyde or hydrogenation of the  $\text{C}=\text{O}$  group to form the unsaturated alcohol. Overhydrogenation of either of these products leads to the saturated alcohol. A decarbonylation pathway is also possible (Rioux, et al., 2006). ..... 37
- Figure 2.21 TEM images for nanoparticles of (a) Au, (b)  $\text{Au}_3\text{Zn}$ , (c)  $\text{Au}_5\text{Zn}_3$ , (d)  $\text{AuZn}$ , and (e)  $\varepsilon\text{-(Au,Zn)}$ . Adapted from (Schaefer, et al., 2010). ..... 39
- Figure 2.22 (A) The rate of propylene oxidation toward propylene oxide (PO), acrolein (Acr), and  $\text{CO}_2$  per surface silver atom (i.e. turnover frequency). (B) Selectivity of propylene oxide, acrolein, and  $\text{CO}_2$  versus temperature. The vertical dashed lines indicate the temperature at which the sintering of the silver trimers begins. Adapted from (Lei, et al., 2010). ..... 41

Figure 3.1	Percentage of terrace sites obtained experimentally from CO-TDS on clean and ethylidyne-covered Pt nanoparticles in comparison to the percentage of highly coordinated (terrace-like) $C^3_9$ and $C^{4,5}_8$ sites obtained from statistics as function of particle size. The inset shows a schematic of a 3nm particle with edge and terrace atoms surface orientations indicated. Adapted from (Lundwall, 2010).....	57
Figure 3.2	Particle size distribution (top), shape distribution (middle) and kinetic data (bottom) for Pt nanoparticles after dispersion on a silica xerogel support and calcination to $T_{calc}=475$ (left) and 575 (right) K. Upon high-T calcination, the Pt nanoparticles take on a more round shape and loose (111) facets (without significant change in particle size), which results in a transition from preferred trans-to-cis isomerization on the catalyst calcined at 475 K, to preferred cis-to-trans conversion on the catalyst calcined at 575 K. Adapted from (Lee, 2009a). .....	60
Figure 3.3	TPR results demonstrating the unique activity of Pt@Ru core-shell catalyst in comparison to an PtRu alloy and a physical mixture of Pt and Ru catalysts. $H_2O$ formation (as percent of maximum) is shown versus temperature for $H_2$ feeds containing 0.1 vol% CO. The insets show the schematic structure of the respective catalyst configurations. Adapted from (Alayoglu, 2008b).....	61
Figure 3.4	Intrinsic turnover frequency vs Pd particle size in aerobic oxidation of benzyl alcohol over a Pd/silica catalyst (left) along with TEM image (middle) and size distribution (right) for a catalyst with average Pd particle size of ~4 nm. Adapted from (Chen, 2008). .....	65
Figure 3.5	Selectivity of Ag nanocubes, nanowires, and nanospheres in epoxidation of ethylene versus inverse characteristic length. TEM images of the nanocubes and nanowires as well as cartoons of all three nanoshapes with dominant surface orientations are shown as well. Adapted from (Christopher, 2010) and (Christopher, 2008) .....	66
Figure 3.6	Phenol yield with time on stream for the parent zeolite (ZSM-5) and the mesoporous zeolite (M-ZSM-5) during hydroxylation of benzene with $N_2O$ to phenol. Creation of mesopores in the zeolite results in a strong decrease in the deactivation rate. Adapted from (Gopalakrishnan, 2008b). .....	69
Figure 3.7	TEM and SEM images and photo of a Pt-BHA coated silica felt catalyst, illustrating hierarchical multiscale catalyst structuring. From left to right: Pt-BHA coated silica felt; SEM image of Pt-BHA coated silica fibers; macropore structure of the supported catalyst (SEM); TEM image of Pt-BHA nanocomposite particulate; and TEM image of Pt nanoparticles embedded in the BHA mesopore structure. From (Sanders, 2008). .....	70
Figure 3.8	Stabilizing metal nanoparticles via alloying: TEM images for Pt-BHA calcined at 500 °C (a) and at 600 °C (b), and PtRh (1:1) calcined at 850 °C (c) and PtRh (3:1) calcined at 700 °C (d). The inset is the EDAX pattern of the larger nanoparticles, showing their identity as pure Pt. From (Cao, 2010c). .....	72



Figure 3.9	TEM images of Pt@mSiO <sub>2</sub> nanoparticles after calcination at 350°C (a) and 750°C (b), and CO oxidation activity of TTAB-capped Pt and Pt@mSiO <sub>2</sub> nanoparticles (c). Adapted from (Joo, 2009).....	73
Figure 3.10	Conceptual scheme of sintering suppression in ceria-supported Pt: On alumina, Pt agglomerates at high temperature, independent of the atmosphere. On ceria, small, active Pt clusters exist at stoichiometric conditions for car exhaust catalysis, while at oxidizing conditions Pt is hindered from agglomeration through oxygen-mediated anchoring on the support. (Scheme adapted from (Shinjoh, 2009a)).....	74
Figure 3.11	Stabilization of a nanocatalyst via addition of a stabilizing oxide coating. CO conversion in CO oxidation for an uncoated (“Au/P25”, circles) and a coated catalyst (“Au/Al <sub>2</sub> O <sub>3</sub> /P25”, squares; inset shows its HRTEM image). Adapted from (Yan, 2005b).....	75
Figure 3.12	PS-b-P4PV scaffolds formed at different conditions (a-c), illustrating the range of structures attainable by Russell’s approach, and silica (d) and titania (e) replicas of the template (c). Adapted from (Chen, 2009).....	79
Figure 3.13	Schematic illustration of the dual nanocasting process resulting in a positive metal oxide replica of a mesoporous silica precursor. ....	80
Figure 3.14	Cubic and tetrahedral (arrows) Pt nanoparticles on a silica support at different temperatures. The rounding of the corners at 350°C indicates the onset of shape loss, which is complete at 500°C. Adapted from (Tao, 2008a).....	84
Figure 3.15	Apparent activation energies and catalytic activities (at 300 °C) of Pt, Au and Cu based catalysts, adapted from (Thinon, 2008). Activity is defined as $F_{CO} \times X_{CO} / W_{cat}$ , where $F_{CO}$ is the molar flow rate of CO, $X_{CO}$ its fractional conversion, and $W_{cat}$ is the catalyst weight. ....	86
Figure 3.16	Schematic illustration of the synthesis of Au supported on ceria nanoshapes, and light-off curves of WGS (in terms of CO conversion) over the three supported Au nanocatalysts on differently shaped ceria supports. Adapted from (Sayle, 2005).....	88
Figure 3.17	Left: Integral alkane desorption signals (normalized to the Pd surface area) as a function of particle size (filled circles) for pentene (a) and ethylene (b) hydrogenation, along with ratio of terrace sites to the total number (N) of surface atoms on the particles (open squares) of the same aspect ratio (height/diameter). The insets in (b) show typical STM images of the Pd nanoparticles and schematic representations of their structures. The lack of particle size dependence of ethylene hydrogenation, and the close correlation between desorption signal and fraction of terrace sites for pentene hydrogenation is apparent. Right: Turnover frequency (TOF) in 1,3-butadiene hydrogenation over different Pd–Al <sub>2</sub> O <sub>3</sub> /NiAl(110) model catalysts as a function of mean particle size, normalized by the total number of Pd surface atoms (c), and normalized by the number of Pd atoms on (111) facets (d) based on a truncated cubo-octahedron as the structural model (shown as inset). The dashed lines show	

	the TOF values for Pd(111) and Pd(110) under identical reaction conditions....	91
Figure 3.18	Schematic illustration of the step-wise functionalization of MWCNT (top) and representative results for ODH of butane and propane. “CNT” denotes the MWCNT as commercially received, “oCNT” the CNT after the first functionalization via HNO <sub>3</sub> reflux, and “P-oCNT” denotes the passivated oCNTs. Adapted from (Zhang, 2008a) and (Frank, 2009).....	94
Figure 4.1	Reaction scheme for hydrogenation of pyrrole. ....	120
Figure 4.2	Pyrrole hydrogenation selectivity for Pt nanocrystals: (Left) For different shape as a function of temperature. Feed was 4 Torr of pyrrole and 400 Torr of H <sub>2</sub> with a He balance; as a function of nanocrystal size. ....	121
Figure 4.3	Conversion in CO oxidation, compared using same weight of ceria. ....	123
Figure 4.4	Dependence of ethylene hydrogenation activity on Pd particle size for Pd/SiO <sub>2</sub> , Pd/TiO <sub>2</sub> , and unsupported Pd. Reaction was carried out at atmospheric pressure at a reaction temperature of 293 K; H <sub>2</sub> and C <sub>2</sub> H <sub>4</sub> concentrations were 8.6 x 10 <sup>-4</sup> mol l <sup>-1</sup> . ....	126
Figure 4.5	Three forms of adsorbed ethylene on noble metals.....	127
Figure 4.6	Reduction profiles of core-shell Rh@Pt, Rh <sub>50</sub> Pt <sub>50</sub> , and monometallic particles, after O <sub>2</sub> treatment, by H <sub>2</sub> or CO. Reduction was measured by evolution of the oxidized reductant as a function of temperature. ....	128
Figure 4.7	(a) Correlation between catalyst lifetime, measured as time when the conversion dropped from 100% to 50%, t <sub>1/2</sub> and external surface area. (b) Coke formation during MTH reactions for ZST-12, and for (c) OSD-5. Internal coke was calculated from the decrease in pore volume after reaction, and external coke was the difference between total coke content and internal coke content.....	131
Figure 4.8a	Structure of the ITQ-2 layers, with the cup-like structure and channels highlighted.....	132
Figure 4.8b	Starting from left. SEM image of multilayer zeolites structures, showing sheet-like material. Right: TEM image of one of the sheets, showing MFI structure.....	133
Figure 4.9	Self-assembled structure of M <sub>4</sub> L <sub>6</sub> , which is capable of stabilizing a cation in the hydrophobic interior. ....	135
Figure 4.10	The addition of nitromethane to p-nitrobenzaldehyde is effectively catalyzed by cooperation between a tethered ureidopropyl group that functions as Lewis acid to render the carbonyl carbon more electrophilic, and an amino group that functions to enhance the nucleophilicity of nitromethane. The curved arrow indicates nucleophilic attack of the nitromethane on the carbonyl carbon. A surface tethered with both groups is catalytically much more active than a surface containing only one group. ....	137

Figure 4.11	In aldol condensation of nitrobenzaldehyde and acetone, H-bonding or protonation of nitrobenzaldehyde by a Brønsted acid enhances the electrophilicity of the carbonyl carbon, whereas H-bonding of the enol form of acetone with a base enhances the nucleophilicity of the $\alpha$ -carbon. ....	138
Figure 4.12	Coupling of ketone with phenol to form the p,p' isomer and the o,p' isomer of bis-phenol A, catalyzed by an acid-base pair. The acid A draws electron from the carbonyl, making it more susceptible to nucleophilic attack. The base B hydrogen-bonds with the hydroxyl, increasing the nucleophilicity of the hydrogen oxygen. ....	138
Figure 4.13	In an isolated Ti metallocene complex for styrene polymerization, the growing chain and the phenyl ring of the last inserted monomer coordinate to the Ti atom, leaving only one free coordination site for an incoming monomer (top). When two Ti complexes are tethered close to each other, the second Ti atom can provide a coordination site to the last phenyl group of the growing chain or the incoming monomer. This results in more facile and/or stronger binding of the incoming monomer to the chain growing Ti atom. Because both the C=C and the phenyl ring can be coordinated to either of the Ti atoms. The net result is faster polymerization rate. ....	139
Figure 4.14	Schematic drawing showing a MgO-Pd-CNT hybrid material that prefers the oil-water interface. The material contains a catalyst on the hydrophilic side to catalyze aqueous phase reactions, and a different catalyst on the hydrophobic side to catalyze organic phase reactions. Reaction intermediates can transfer from one phase to another, thus enabling a one-step process of a sequential reaction in which different steps take place in different phases. ....	141

## TABLES

Table 3.1	Select Catalyst Systems Synthesized via Flame Pyrolysis and Their Catalytic Application (adapted from Strobel, 2009).....	76
Table 3.2	Propane Conversion, Propene Selectivity, and Turnover Frequencies for the Pt <sub>8-10</sub> Cluster Catalyst in Comparison to a Conventional Pt/alumina Monolith Catalyst and a VOx/Al <sub>2</sub> O <sub>3</sub> Catalyst. Adapted from (Vajda, 2009) .....	93
Table 4.1	CO Oxidation Activity and Properties of CeO <sub>2</sub> of Different Shapes .....	123
Table 4.2	Properties of Conventional (ZST-12) and Mesoporous (OSD-2 and OSD-5) ZSM-5. ....	130
Table 4.3	Activity Comparison of ITQ-2 and H-ZSM-5 and H-MOR for Coupling of 2-Methylnaphthalene and Paraformaldehyde .....	134
Table 4.4	Comparison of Catalytic Activities, Measured as Conversion, of Mesoporous Zeolites Constructed from Nanosheets with Conventional Sample.....	134

Table 4.5	Effect of Distance of a Thiol Group on the Activity of a Sulfonic Group-catalyzed Coupling of Ketone with Phenol to Form Bis-phenol-A.....	138
Table 4.6	Other Examples Illustrating Dependence of Catalytic Properties on Various Size-Dependent Material Properties.....	142

### ***The Catalytic Advances Program (CAP)***

CAP is the industry's leading membership-driven program which serves an information resource for R&D and commercial organizations in the catalyst and process industries. Companies that join CAP combine their resources to jointly explore the world's most promising catalytic technologies. Members receive three in-depth **CAP Technical Reports** which are written by leading scientists and experienced industry professionals in areas selected by the membership (via ballot); weekly *CAP Communications* (delivered via e-mail), which provide the latest updates on technical breakthroughs, commercial events and exclusive development opportunities; and attendance at the CAP Annual Meeting.

The *Catalytic Advances Program (CAP)* is available on a membership basis from The Catalyst Group Resources (TCGR). For further details, please contact John J. Murphy at [John.J.Murphy@catalystgrp.com](mailto:John.J.Murphy@catalystgrp.com) or +1.215.628.4447.



P.O. Box 680  
Spring House, PA 19477 U.S.A  
ph: +1.215.628.4447  
fax: +1.215.628.2267  
website: [www.catalystgrp.com](http://www.catalystgrp.com)